

### General Product Description

The extra-high tough steel for structural wear parts

Hardox® HiTuf is an abrasion-resistant plate with guaranteed impact toughness. With a nominal hardness of 350 HBW, it's a good choice for structural wear parts like thick cutting edges, demolition tools and rippers.

### Dimension Range

Hardox® HiTuf is available in thicknesses of 40.0 - 160.0 mm. Hardox® HiTuf is available in widths up to 3350 mm and lengths up to 14630 mm. For thicknesses over 125 mm preferred width is 1650 mm. More detailed information on dimensions is provided in the dimension program.

### Mechanical Properties

| Product       | Thickness (mm) | Hardness <sup>1)</sup> (HBW) | Typical yield strength (MPa), not guaranteed |
|---------------|----------------|------------------------------|--|
| Hardox® HiTuf | 40.0 - 160.0   | 310 - 370                    | 850  |

<sup>1)</sup> Brinell hardness, HBW, according to EN ISO 6506-1, on a milled surface 0.5 – 3 mm below surface for plate. At least one test specimen per heat and 40 tons.

The nominal material thickness will not deviate more than ± 15 mm from that of the test specimen.

Hardox® wear plate is through-hardened. Minimum core hardness is 90 % of the guaranteed minimum surface hardness.

### Impact Properties

| Product       | Min impact energy for transversal testing, Charpy V 10x10 mm test specimen <sup>1)</sup> |
|---------------|--|
| Hardox® HiTuf | 40 J / -40 °C  |

<sup>1)</sup> Impact testing according to ISO EN 148 per heat and thickness group. Average of three tests. Single value minimum 70% of specified average.

### Chemical Composition (heat analysis)

| C <sup>*)</sup> (max %) | Si <sup>*)</sup> (max %) | Mn <sup>*)</sup> (max %) | P (max %) | S (max %) | Cr <sup>*)</sup> (max %) | Ni <sup>*)</sup> (max %) | Mo <sup>*)</sup> (max %) | B <sup>*)</sup> (max %) |
|-------------------------|--------------------------|--------------------------|-----------|-----------|--------------------------|--------------------------|--------------------------|-------------------------|
| 0.20                    | 0.60                     | 1.60                     | 0.050     | 0.020     | 0.70                     | 2.0                      | 0.70                     | 0.005                   |

The steel is grain refined. <sup>\*)</sup> Intentional alloying elements.

### Carbon Equivalent CET(CEV)

| Thickness (mm) | 40.0 - 70.0 | 70.1 - 160.0 |
|----------------|-------------|--------------|
| Max CET(CEV)   | 0.38 (0.56) | 0.41 (0.67)  |
| Typ CET(CEV)   | 0.36 (0.55) | 0.39 (0.64)  |

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

## Tolerances

More details are given in SSAB's brochure Hardox® Guarantees or at [www.ssab.com](http://www.ssab.com).

### Thickness

Tolerances according to Hardox® Thickness Guarantees.

Hardox® Guarantees meet the requirements of EN 10029 Class A, but offer more narrow tolerances.

### Length and Width

According to SSAB's dimension program. Tolerances conforms to EN 10029 or to SSAB's standard after agreement.

### Shape

Tolerances according to EN 10029.

### Flatness

Tolerances according to Hardox® Flatness Guarantees Class C, which are more restrictive than EN 10029 class N.

### Surface Properties

According to EN 10163-2 Class A, Subclass 1.

## Delivery Conditions

The delivery condition is Quenched. The plates are delivered with sheared or thermally cut edges. Untrimmed edges after agreement.

Delivery requirements can be found in SSAB's brochure Hardox® Guarantees or [www.ssab.com](http://www.ssab.com).

## Fabrication and Other Recommendations

### Welding, bending and machining

Recommendations can be found in SSAB's brochures at [www.hardox.com](http://www.hardox.com) or consult Tech Support.

Hardox® HiTuf is not intend for further heat treatment. It has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 450°C .

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.

## Contact Information

[www.ssab.com/contact](http://www.ssab.com/contact)